

## DNG 205 Series Non-Woven Geotextile

DeWitt DNG205 is an 8 oz needlepunched non-woven polypropylene geotextile made of 100% polypropylene staple fibers, which are formed into a random network for dimensional stability. The fabric resists ultraviolet deterioration, rotting, biological degradation, naturally encountered basics and acids.

Properties	<b>Test Method</b>	Unit	Minimum Average Roll Value
Weight	ASTM D 5261	$OZ/YD^2 (G/M^2)$	8.0 (271)
Grab Tensile	ASTM D 4632	LBS	205
Grab Elongation	ASTM D 4632	%	50
Trapezoid Tear Strength	ASTM D 4533	LBS	85
CBR Puncture Resistance	ASTM D 6241	LBS	535
Permittivity*	ASTM D 4491	SEC <sup>-1</sup>	1.35
Water Flow*	ASTM D 4491	GPM/FT <sup>2</sup>	90
AOS*	ASTM D 4751	US SIEVE	80
UV Resistance	ASTM D 4355	%/HRS	70/500

## **Primary Application: Stabilization and Permanent Erosion Control**

Date: 06/01/23. This data sheet supersedes all previously issued data. The above properties are typical averages.

THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR IN ANY PROCESS, SUCH INFORMATION IS TO THE BEST OF OUR KNOWLEDGE AND BELIEF, ACCURATE AND RELIABLE AS THE DATE COMPLIED. HOWEVER NO REPRESENTATION, WARRANTY OR GUARANTEE IS MADE AS TO ITS ACCURACY, RELIABILITY OR COMPLETENESS. IT IS THE USER'S RESPONSIBILTY TO SATISIFY HIMSELF AS TO THE SUITABILITY AND COMPLETENESS OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE. WE DO NOT ACCEPT LIABILITY FOR ANY LOSS OR DAMAGE THAT MAY OCCUR FROM THE USE OF THIS INFORMATION NOR DO WE OFFER ANY WARRANTY AGAINST PATENT INFRINGEMENT.



<sup>\*</sup>At the time of manufacturing. Handling may change these properties